

# **Multisil**\*

# silicone sealant

### **Product Description**

Multisil silicone is a one-part, low modulus silicone sealant that has a neutral cure when exposed to atmospheric moisture. The resulting rubber-like seal exhibits high elasticity and excellent durability against sunlight, UV radiation, rain, snow and temperature extremes.

Multisil silicone provides good adhesion to most common building materials such as: glass or glazed surfaces, aluminium and other metals, masonry, treated wood, concrete, PVC and many other plastics without the use of a primer.†

### **Typical Performance Properties**


- UV resistant
- Excellent durability
- Unaffected by high or low temperatures
- Resistant to weathering
- 100% silicone
- Low-modulus
- High elasticity
- Fast curing
- High movement capability
- Low odor

## **Potential Applications**

- Glazing
- Construction
- Joint Sealing
- Bonding
- Assembly

† Qualification testing is advised. In certain cases the use of a primer may be required.









### **PRODUCT** DATA

General Product Data	UOM		Results
Cartridge Availability	ml		310
Foils Availability	ml		On request
Colors Available			On request
Curing System			Neutral
Uncured Product Data	UOM	Procedure	Results
cific Gravity			1.03
Application Rate	g/minute	6 mm orifice, 2 bar pressure	400
Sag	mm	ISO 7390	<2
Tooling Time	minutes	at 23 °C, 50% RH	10
Tack Free Time	minutes	at 23 °C, 50% RH	20
Shelflife	months		13
Application temperature	(°C)		+5 / +40
Cured Product Data	UOM	Procedure	Results
Hardness (Shore A)	Shore A	DIN 53505	20
Full Cure	days		1 - 5
Tensile Strength	MPa	ASTM D 412 (die C)	1.2
Tensile modulus @ 100% elongation	MPa	ASTM D 412 (die C)	0.3
Elongation at break	%	ASTM D 412 (die C)	550
Tensile adhesion modulus @ 100% elongation	MPa	ISO 8339 (glass substrates)	0.32
Tensile adhesion strength at break	MPa	ISO 8339 (glass substrates)	0.56
Tensile elongation at break	%	ISO 8339 (glass substrates)	300
Peel adhesion strength	Kn/m	ASTM C 794	6
Temperature resistance	(°C)		-50 / +100

**CERTIFICATION** EN15651-1 Type F INT-EXT class 25LM

EN15651-2 Type G class 25LM

SNJF Vitrage no 345

SNJF Facade no 344 Classe F25E/G25E with or without primer

### **HANDLING & SAFETY**

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.ge.com/silicones or, upon request, from any MPM representative. Use of other materials in conjunction with MPM sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

# **FOR USE**

INSTRUCTIONS Surface must be clean, dry and free from oil, grease, dust and other loose matter. Detergent or soap and water treatments are not recommended. Surfaces should be cleaned with alcohol, M.E.K. or other suitable solvent. The solvent used should be checked for compatibility with adjacent materials that it will contact.

INFORMATION Europe, Middle East, Africa and India: +00 800 4321 1000 | Americas: +1 800 295 2392. Asia Pacific: Japan: +81 276 20 6182, China: +800 820 0202, All APAC: +60 3 9206 1543

### DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SURSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER") THE MIRE BLACK, PRODUCTS AND SERVICES OF MOMENTING FEB PRIMARY ENVIRONMENTALS INC. AND ITS SUBJECT TO SUPPLIER SCAPE AND APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALL HOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (1) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (1) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

GE is a trademark of General Electric Company and is under license by Momentive Performance Materials Inc., Huntersville, NC 28078 \*Trademark of Momentive Performance Materials Inc.

Copyright 2007-2015 Momentive Performance Materials, Inc. All rights reserved. 08/15 161-082-00